



PVCu Gap Filler

Revision: 3/12/20 Page 1 from 1

Technical data

Basis	PVC resin
Consistency	Paste
Curing system	Physical drying
Movement accommodation	+ or – 7.5%
Skinning time (20°C)	Ca. 5 to 10 mins
Cure time	1-2 Days
Temperature resistance**	- 20°C to +80°C
Application temperature	+ 5°C to + 30°C
Minimum Joint Width	2mm
Maximum Joint Width	6mm

^{*} These values may vary depending on environmental factors such as temperature, moisture, and type of substrates. ** This information relates to fully cured product.

Product description

Small Gap Filler is an easily applied, one-part solvent-based paste. It is ideal for filling joints between PVCu and joint sealing. Outstanding adhesion to most construction substrates, reacting through solvent evaporation to form a durable and flexible seal.

Properties

- Solvent based
- Easy applied
- Outstanding adhesion
- Durable and flexible seal
- Paintable with most paints

Applications

Surfaces must be sound, clean and dry Gun the sealant firmly into the joint. The sealant may be tooled using a wet spatula. Tack free in approx. 5 minutes and fully cured in 1 to 2 days depending on joint dimensions

Remove any surplus material immediately using Soudal Foam and Gun Cleaner or Swipex.

Packaging

Colour: White

Packaging: 300ml Cartridge

Shelf life

At least 12 months in unopened packaging in a cool, dry and frost-free storage place at temperatures between +5 °C and +25 °C.

Substrates

Substrates: PVCu

Surface preparation: Surfaces must be clean

and dry before application.

We recommend a preliminary adhesion test on any substrate.

Application method

Application method: Gun sealant firmly into the joint. May be applied with a wet spatula. Cleaning: Soudal Foam and Gun Cleaner Repair: Same material

Health- and Safety Recommendations

Take the usual labour hygiene into account. Consult label and material safety data sheet for more information.

Remarks

Small Gap Filler must not be used:

- · bedding of sealed units
- to manufacture aquariums

Remark: This technical data sheet replaces al previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

 Soudal NV
 Everdongenlaan 18 - 20
 B-2300 Turnhout, Belgium

 Tel: +32 (0)14-42.42.31
 Fax: +32 (0)14-42.65.14
 www.soudal.com